

(11) EP 0 926 199 A1

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
30.06.1999 Bulletin 1999/26

(51) Int. Cl.⁶: C08L 77/00, C08K 3/04,
B60K 15/04

(21) Application number: 98124445.2

(22) Date of filing: 22.12.1998

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 24.12.1997 JP 36716397

(71) Applicants:
• TOYODA GOSEI CO., LTD.
Nishikasuga-gun Aichi-ken (JP)
• Mitsubishi Chemical Corporation
Chiyoda-ku, Tokyo (JP)

(72) Inventors:
• Hagano, Hiroyuki
Inazawa-shi, Aichi-ken (JP)
• Nakagawa, Masayuki
Iwakura-shi, Aichi-ken (JP)
• Hisashi, Hideyuki,
Mitsubishi Chemical Corporation
Yokkaichi-shi, Mie-ken (JP)
• Morimoto, Seiji
Hiratsuka-shi, Kanagawa-ken (JP)

(74) Representative: HOFFMANN - EITL
Patent- und Rechtsanwälte
Arabellastrasse 4
81925 München (DE)

(54) Polyamide composition and fuel tank caps made of the same

(57) The present invention relates to a polyamide resin composition comprising a polyamide resin, a modified ethylene copolymer, an amide-based dispersant and an electroconductive material,

said composition having not more than $10^{11} \Omega \cdot \text{cm}$ of an intrinsic volume resistivity and not less than 30 KJ/cm^2 of an Izod impact strength measured according to ASTM D256.

FIG.1





FIG.2



EP 0 926 199 A1

FIG.3





FIG.4



Description

BACKGROUND OF THE INVENTION

5 [0001] The present invention relates to a polyamide resin composition and fuel tank saps made of the same. More particularly, it relates to a novel polyamide resin composition having excellent impact strength, electroconductivity and lightweight properties. This polyamide resin composition is useful for various articles such as fuel tank caps, hoses for solvents such as gasoline, various types of connectors, door handle parts, etc.

10 [0002] There are known the fuel tank caps of various structures for use in many fields of industry. FIG. 1 shows a sectional illustration of an ordinary type of cap used for the fuel tanks of automobiles.

[0003] The cap 2 shown in FIG. 1 principally comprises a resin-made closure 3 which fits on a fuel filler neck 1 which opens when feeding fuel and a resin-made shell 14 covering the upper part of the closure 3.

[0004] The closure 3 comprises a cylindrical portion 4 and a top plate 8 disposed so as to close the inner periphery of the cylindrical portion at its substantially middle position in the vertical direction and having an overflow opening 9 at the center. At the outer periphery of the lower part of the cylindrical portion 4 is formed a thread 5, to engage with the filler neck 1. At the outer periphery of the upper part of the cylindrical portion 4 is formed a flange 6 adapted to detain the resin-made shell 14 in position. Beneath the flange 6 is secured a seal ring 7.

[0005] A valve body 10 constituting a negative pressure valve is disposed on the lower side of the top plate 8 in the inside of the cylindrical portion 4. The valve body 10 is held in position by a holder plate 11 which is given an upward urge by a coiled spring 12 secured to a spring seat plate 13.

20 [0006] The cap 2 of the above construction is set in position as its resin-made closure 3 is fitted on the filler neck 1 disposed in its mounting hole 17 formed in a fixture 16 in a fuel lid 15 of an automobile. In FIG. 1, reference numeral 18 indicates the body of an automobile, 19 a fuel feed port, and 20 the chassis of the automobile.

[0007] The conventional fuel tank caps have no electroconductivity and are therefore incapable of discharging static electricity which may be charged on the human body or clothes every time when the cap is handled. In order to solve this static charge problem, attempts have been made to impart electroconductive properties to the caps by blending an electroconductive material such as carbon black or carbon whisker into a lightweight and high-strength polyamide resin.

25 [0008] These attempts still have the problem that when an electroconductive material such as carbon black necessary for imparting electroconductivity of not more than $10^{11} \Omega \cdot \text{cm}$ (as volume resistivity) required for the fuel tank caps is blended in a basic polyamide resin, the melt viscosity of the resin composition increases, so that it is difficult to conduct its operation such as injection molding. Even if the molding operation could be performed, the molded product is deteriorated in its mechanical properties such as impact strength and hardly capable of attaining an Izod impact strength (ASTM D256) of not less than 30 KJ/m^2 required for the fuel tank caps.

[0009] It is known to blend a modified polyethylene copolymer in a polyamide resin to improve impact resistance.

35 [0010] However, there is yet available no impact-resistant electroconductive polyamide resin composition having satisfactory impact strength while maintaining electroconductivity required for the fuel tank caps by blending an electroconductive material such as carbon black and suited for use as material of fuel tank caps.

40 [0011] As a result of the present inventors' earnest studies to solve the above problem, it has been found that a resin composition comprising a polyamide resin, a modified ethylene copolymer, an amide-based dispersant and an electroconductive material, shows satisfactory impact strength and electroconductivity. The present invention has been attained on the basis of the above finding.

SUMMARY OF THE INVENTION

45 [0012] The object of the present invention is to provide a polyamide resin composition which is light in weight and yet has a sufficient electroconductivity, a good molding workability, a high modulus of elasticity and a high impact strength, and its use as molding material for fuel tank caps in particular.

[0013] In order to attain the above object, in a first aspect of the present invention, there is provided a polyamide resin composition comprising a polyamide resin, a modified ethylene copolymer, an amide-based dispersant and an electroconductive material,

the said composition having not more than $10^{11} \Omega \cdot \text{cm}$ of an intrinsic volume resistivity and not less than 30 KJ/cm^2 of an Izod impact strength measured according to ASTM D256.

55 [0014] In a second aspect of the present invention, there is provided a fuel tank cap comprising an impact-resistant electroconductive polyamide resin composition comprising a polyamide resin, a modified ethylene copolymer, an amide-based dispersant and an electroconductive material, the said composition having a volume resistivity of not more than $10^{11} \Omega \cdot \text{cm}$ and an Izod impact strength according to ASTM D256 of not less than 30 KJ/m^2 .

[0015] In a third aspect of the present invention, there is provided a use of an impact-resistant electroconductive polyamide resin composition comprising a polyamide resin, a modified ethylene copolymer, an amide-based dispersant and an electroconductive material,

the said composition having not more than $10^{11} \Omega \cdot \text{cm}$ of an intrinsic volume resistivity and not less than 30 KJ/cm^2 of an Izod impact strength measured according to ASTM D256, for producing fuel tank caps.

BRIEF DESCRIPTION OF THE DRAWINGS

[0016]

FIG. 1 is a sectional illustration of an example of ordinary caps for the fuel tanks of automobiles and others.

FIG. 2 is a sectional illustration of another example of caps for the fuel tanks of automobiles and others.

FIG. 3 is a sectional illustration of still another example of caps for the fuel tanks of automobiles and others.

FIG. 4 is an illustration of the method of measurement of volume resistivity of a resin-made shell (outer shell) according to ASTM D257.

DETAILED DESCRIPTION OF THE INVENTION

[0017] The present invention is described in detail below.

[0018] The fuel tank caps comprising a polyamide resin according to the present invention can be utilized for a variety of purposes in many fields of industry. The main feature according to the present invention lies in the composing material and, therefore, their structure and shape are not restricted. The fuel tank caps of the present invention is particularly useful for application to the fuel (gasoline) tanks of automobiles and the like. A typical example of the fuel tank caps for automobiles and the like comprises a resin-made closure designed to fit on a fuel filler neck and a resin-made shell covering the upper part of the said closure. An example of the structure of this type of a cap is illustrated in FIG. 1, which was briefly explained above.

[0019] In a fuel tank cap principally comprising a filler neck 1, a resin-made closure 3 designed to fit on the filler neck 1 and a resin-made shell 14, it is not necessary that both of the resin-made closure 3 and the resin-made shell 14 comprise the impact-resist electroconductive polyamide resin composition of the present invention which is described later; as far as at least the shell 14 is made of the said resin composition. However, in order to maximize the static electricity discharging function of the cap, it is preferable that both of the closure 3 and the shell 14 comprises the said resin composition.

[0020] Also, in the said fuel tank cap mainly comprising a resin-made closure 3 fitting on a filler neck 1 and a resin-made shell 14, it is preferable that the resin-made shell 14 be imparted with a static electricity discharging route. Such a discharge circuit is preferably established by making conductive the resin-made shell 14 and filler neck 1 or the chassis body 20. FIGS. 2 and 3 are the sectional illustrations of the other examples of the caps used for the fuel tanks of automobiles, etc., and these figures show the said static electricity discharge route. In the case of the discharge circuit shown in FIG. 2, the static electricity is discharged to the filler neck 1 through a retainer 23, and in the case of the discharge circuit shown in FIG. 3, the static electricity is discharged to the chassis body 20 through a string conductor 26. It is possible to effect discharge by connecting the retainer 23 and the string conductor 26 as shown by a dotted line in FIG. 3. In FIG. 2, reference numeral 23a indicates an internal engaging section, 23b a ring member, and 34a an external engaging section.

[0021] The feature of the fuel tank cap according to the present invention is to use a resin composition for producing the cap of the type described above, which resin composition comprises a polyamide resin, a modified ethylene copolymer, an amide-based dispersant and an electroconductive material, and has impact-resistant and electroconductive with a volume resistivity of not more than $10^{11} \Omega \cdot \text{cm}$ and an Izod impact strength (measured according to ASTM D256) of not less than 30 KJ/cm^2 . This polyamide resin composition also has a high bending modulus of usually not less than 10,000 as measured according to ASTM D790) and good moldability.

[0022] The polyamide resins usable in the present invention include nylons 4, 6, 7, 8, 11, 12, 6-6, 6-10, 6-11, 6-12, 6T, 6/6-6, 6/12, 6/6T, 6/12T and the like. Nylon 6 is preferred in view of cost and impact resistance. The reduced viscosity (η_{rel}) of the polyamide resin used in the present invention is preferably 2.2 to 3.5. If the reduced viscosity of the polyamide resin used is less than 2.2, the produced composition may be unsatisfactory in impact resistance. If the reduced viscosity exceeds 3.5, the fluidity of the composition may be deteriorated to impair its moldability. In the present invention, nylon 6 having a reduced viscosity of 2.2 to 3.5 is especially preferred for use as the polyamide resin.

[0023] The modified ethylene copolymer used in the present invention can be obtained by graft-polymerizing an α, β -unsaturated carboxylic acid or a derivative thereof to a copolymer of ethylene and an α -olefin having 3 or more carbon atoms (hereinafter referred to as "unmodified ethylene copolymer") in an amount of usually 0.05 to 1.5% by weight

based on the unmodified ethylene copolymer.

[0024] The said unmodified ethylene copolymer can be obtained by copolymerizing ethylene of usually not less than 50 mol%, preferably 80 to 95 mol% with an α -olefin having 3 or more carbon atoms of usually not more than 50 mol%, preferably 20 to 5 mol% of in the presence of a Ziegler-Natta catalyst, preferably a vanadium compound such as vanadium oxytrichloride or vanadium tetrachloride and an organoaluminum compound. Examples of the α -olefins having 3 or more carbon atoms usable for the above copolymerization include propylene, butene-1, hexene-1, decene-1, 4-methylbutene-1, 4-methylpentene-1 and the like. Propylene or butene-1 is preferred.

[0025] Preferred examples of the unmodified ethylene copolymers usable for the said purpose include a series of resins commercially available under the trademark of "Tafmer" by Mitsui Petrochemical Co., Ltd., which include "Tafmer A" series (ethylene-butene-1 copolymers) such as "Tafmer A4085", "Tafmer A4090" and "Tafmer A20090", and "Tafmer P" series (ethylene-propylene copolymers) such as "Tafmer P0280", "Tafmer P0480", "Tafmer P0680" and "Tafmer P0880".


[0026] As the α,β -unsaturated carboxylic acid or a derivative thereof (hereinafter referred to as "unsaturated carboxylic acid") to be graft polymerized to the said unmodified ethylene copolymer, there can be used, for instance, acrylic acid, methacrylic acid, ethacrylic acid, maleic acid, fumaric acid and anhydrides or esters of these acids, of which maleic anhydride is preferred.

[0027] The amount of the unsaturated carboxylic acid to be grafted is usually 0.05 to 1.5% by weight, preferably 0.1 to 1% by weight based on the unmodified ethylene copolymer. If the amount of the unsaturated carboxylic acid is less than 0.05% by weight, the effect of improving impact resistance may be small and it may be impossible to obtain the molded products having a large tensile elongation. Also, because of poor compatibility with polyamides, the molded products tend to suffer surface exfoliation. The amount of the unsaturated carboxylic acid exceeds 1.5% by weight tends to cause tinting of the composition.

[0028] Graft polymerization is carried out by adding an unsaturated carboxylic acid to an unmodified ethylene copolymer, melting and kneading the mixture usually at a temperature of 150 to 300°C according to the conventional methods. In carrying out this graft polymerization, an organic peroxide such as α,α' -bis-1-butylperoxy-p-diisopropylbenzene may be used to obtain a good yield of the polymerization. In this case, the amount of the organic peroxide used is usually 0.001 to 0.05% by weight based on the unmodified ethylene copolymer.

[0029] The degree of crystallinity of the modified ethylene copolymer used in the present invention is usually not more than 75%, preferably 1 to 35%, and the melt index thereof is usually within the range of 0.01 to 50, preferably 0.1 to 20. The above degree of crystallinity was determined according to the X-ray method described in Journal of Polymer Science, Vol. XVII (1955), pp. 17-26, and the melt index was determined according to the method of ASTM D-1238 57T at 190°C. The above-described modified ethylene copolymers can be obtained using the unmodified ethylene copolymers having a degree of crystallinity and a melt index within the above-defined ranges. The reduced viscosity of the modified ethylene copolymer is preferably 2.2 to 3.5. When the reduced viscosity of the said copolymer is less than 2.2, the produced composition tends to be unsatisfactorily low in impact strength, and when the reduced viscosity exceeds 3.5, fluidity of the composition tends to deteriorate to impair its moldability.

[0030] The amide-based dispersant used in the present invention is not specified, but N-alkylarylsulfoneamides, especially those represented by the following formula are preferably used.



[0031] Where R^1 is a hydrogen atom or a lower alkyl group, R^2 is a lower alkyl group or a cycloalkyl group, and R^3 is a hydrogen atom, a lower alkyl group or a cycloalkyl group. The lower alkyl group is preferably C_1 - C_6 alkyl group and the cycloalkyl group is preferably C_6 - C_{12} cycloalkyl group.

[0032] Examples of the N-alkylarylsulfoneamides represented by the above formula include N-n-butylbenzenesulfoneamide, N-n-propylbenzenesulfoneamide, N-ethylbenzenesulfoneamide, N-cyclopentylbenzenesulfoneamide, N-cyclohexylbenzenesulfoneamide, N-n-butyltoluenesulfoneamide, N-cyclohexyltoluenesulfoneamide, N,N'-dimethylbenzenesulfoneamide, N,N'-diethylbenzenesulfoneamide, N,N'-dipropylbenzenesulfoneamide, N,N'-di-n-butylbenzenesulfoneamide, N,N'-methylethylbenzenesulfoneamide, N,N'-methylpropylbenzenesulfoneamide, and N,N'-ethylpropylbenzenesulfoneamide.

[0033] As the electroconductive material in the present invention, carbon black, electroconductive potassium titanate

whisker, carbon whisker and the like can be preferably used. Carbon black is more preferred.

[0034] As the said electroconductive potassium titanate whisker, any type thereof can be used provided that the surfaces of the potassium titanate whiskers of the formula: $K_2O \cdot nTiO_2$, have been subjected to an electroconductive treatment, but the white whiskers coated with tin oxide or antimony oxide or the black whiskers obtained by depositing carbon on the surfaces of the potassium titanate whiskers are preferably used. Specifically, a commercial product available under the trade name of "Dental" by Otsuka Chemical Co., Ltd. can be used.

[0035] As for the carbon black used in the present invention, various types of carbon black which are shown in "Handbook of Carbon Black, 3rd Ed." published by the Japan Carbon Black Association in 1995, and have a total amount of oxygen from volatiles of not more than 25 mg/g and a UV absorbance of not more than 0.15, are preferably used.

[0036] A preferred method for obtaining such carbon black having good electroconductivity comprises heat-treating furnace black with a total pre-treatment amount of oxygen of not more than 50 mg/g, preferably not more than 20 mg/g, under an inert atmosphere to reduce the total amount of oxygen. The term "inert atmosphere" herein means an atmosphere where there exist no oxygen molecules, or if they exist, their compositional percentage is very low. Specifically, an atmosphere comprising argon, nitrogen, carbon dioxide or such is preferred. The temperature for the heat treatment is preferably 200 to 700°C. When the temperature is less than 200°C, it may be hardly possible to eliminate the oxygen functional groups. When the temperature exceeds 700°C, there may take place thermal shrinking of the carbon black particle surfaces as well as the aggregates or agglomerates of the particles, so that by the hardening of the agglomeration units, their dispersibility in the resin may be deteriorated. The heat-treating time, although variable depending on the atmosphere temperature, is preferably about 15 minutes to 10 hours.

[0037] The oxygen functional groups such as hydroxyl groups or carbonyl groups exist in the carbon black particle surfaces, and the amount of such functional groups greatly affects resistance when such carbon black is blended in a resin. Usually, the amount of the oxygen functional groups is determined from the volatile composition, the amount of hydroxyl or carbonyl groups from CO, and the amount of carboxyl groups from CO_2 , and the total amount of oxygen is calculated from CO and CO_2 .

[0038] The said volatile composition can be determined in the following way. First, a preliminarily determined amount of dry carbon black is put into a heat-resistant test tube, evacuated to 10 to 2 mmHg, and then set in a 1,500°C electric furnace, allowing elimination of the volatiles for 30 minutes. Then the whole amount of the eliminated components are collected and mixed in a tank, and gas-chromatograph measured thereof is conducted to determine the gas composition and the amounts of its components. The total amount of oxygen (total oxygen) is calculated from the results of the above determinations.

[0039] Carbon black is a carbonaceous material which is infinitely close to the condition of purity, but by fine analysis thereof, the materials which are carbon black precursors such as pyrene, naphthalene and fluoranthene are present on the surfaces or the inside of the particles. The amounts of these materials can be known by determining ultraviolet absorbance, in the following way for instance. First, 3.00 g of carbon black is supplied into a Erlenmeyer flask, then 30 ml of toluene is added thereto, and the mixed solution is shaken for 60 seconds and then passed through a filter paper (either of the two types specified in JIS P3801). Then the filtrate is put into a flow cell and absorbance at the measuring wavelength of 336 nm is measured. The higher the absorbance, the more the amounts of the precursors increase.

[0040] According to V. E. Gool et al (Study of Electroconductive Polymers and Their Application, 1970), it is considered that the transfer of electric charge necessary for causing flow of electricity takes place mostly on the surfaces of the chains constituted by the filler particles and in the particles by using radiant heat. The oxygen functional groups present on the carbon black surface and the carbon black precursors such as pyrene determined by UV absorbance are the materials which obstruct the transfer of electric charges, and it is considered that the more the amount of such materials, the more the electroconductivity worsens. As a result of various studies based on the above conception, it was found that the carbon black with a total amount of oxygen of not more than 25 mg/g and a UV absorbance of not more than 0.15 mg is an electroconductive material especially preferred for the purpose of the present invention.

[0041] In the present invention, although one type of carbon black may be used, it is preferred to use a combination of two or more types of carbon black having a different specific surface of not less than 500 m^2/g from each other for the following reason.

[0042] Generally, carbon black having a high specific surface area is produced by subjecting the base carbon black to activation or other treatments, and in such carbon black many pores are present in the surface and the inside of the particles. In carbon black having a large number of such pores, the number of the carbon black particles per unit weight is large, so that in a resin matrix where a prescribed amount of carbon black was blended, the frequency of contact between the carbon black particles is high, and hence a resin matrix having a composition of low resistance is obtained. On the other hand, since such carbon black adsorbs the low-molecular weight materials and dispersant blended in the resin, it tends to deteriorate the properties other than electroconductivity of the composition. Quite surprisingly, however, it has been found that a system comprising 10 to 60 wt% of carbon black of high specific surface area and 40 to 90 wt% of carbon black of low specific surface area derives only the good properties of both types of carbon black.

[0043] The impact-resistant electroconductive polyamide resin composition for fuel tank caps according to the present

invention comprises a blend of the said types of polyamide resin, modified ethylene copolymer, amide-based dispersant and electroconductive material. The blending method and the amounts of the respective components to be blended are not specifically defined as far as satisfying the requirement that the obtained resin composition has a volume resistivity of not more than $10^{11} \Omega \cdot \text{cm}$ and an Izod impact strength (measured according to ASTM D256) of not less than 30 KJ/m². But, the following procedures are preferred.

[0044] Generally, the content of the modified ethylene copolymer is 10 to 120 parts by weight based on 100 parts by weight of the polyamide resin. The amount of the amide-based dispersant in the whole composition is 1 to 15% by weight based on the weight of the impact-resistant electroconductive polyamide composition, and the amount of the electroconductive material in the whole composition is 8 to 35% by weight based on the weight of the impact-resistant electroconductive polyamide composition.

[0045] If the amount of the amide-based dispersant is less than 1% by weight, sufficient kneading may not be attained especially for a blend system required for such a conductive composition where carbon black is blended in a high content, and consequently, it may become difficult to obtain such a resin composition with good dispersibility and high electroconductivity. On the other hand, if the percentage of the amide-based dispersant exceeds 15% by weight, the content of carbon black to the resin becomes high excessively to adversely affect impact resistance of the composition. The preferred amount of the amide-based dispersant is 3 to 10% by weight.

[0046] If the amount of the electroconductive material is less than 8% by weight, antistatic properties of the composition tend to deteriorate, and if the amount exceeds 35% by weight, the kneading operation may become hard to conduct normally, and it also may become difficult to maintain preferred fluidity and mechanical strength of the composition.

The preferred percentage of the electroconductive material is 10 to 30% by weight based on the weight of the impact-resistant electroconductive polyamide composition.

[0047] In case where a modified ethylene copolymer containing propylene as repeating units is used, the content of the propylene-containing modified ethylene copolymer is preferably 10 to 40 parts by weight based on 100 parts by weight of the polyamide resin, the amount of the amide-based dispersant in the whole composition is preferably 1 to 15% by weight, and the amount of the electroconductive material in the whole composition is preferably 8 to 35% by weight.

[0048] In case where a modified ethylene copolymer containing butene-1 as repeating units is used, the content of the butene-1-containing modified ethylene copolymer is preferably 50 to 120 parts by weight based on 100 parts by weight of the polyamide resin, the amount of the amide-based dispersant in the whole composition is preferably 1 to 15% by weight, and the amount of the electroconductive material in the whole composition is preferably 8 to 35% by weight.

[0049] In case both of the said propylene-containing modified ethylene copolymer and butene-1-containing modified ethylene copolymer are used, the content of propylene-containing modified ethylene copolymer is preferably 10 to 40 parts by weight based on 100 parts by weight of the polyamide resin, the content of the butene-1-containing modified ethylene copolymer is preferably 50 to 120 parts by weight based on 100 parts by weight of the polyamide resin, the amount of the amide-based dispersant in the whole composition is preferably 1 to 15% by weight, and the amount of the electroconductive material in the whole composition is 8 to 35% by weight.

[0050] In either case, it is preferable that the matrix resin is an impact-resistant polyamide resin modified by a modified ethylene copolymer. Especially, an impact-resistant polyamide resin modified by a propylene-containing modified ethylene copolymer has an excellent modulus of elasticity that can never be obtained with an impact-resistant polyamide resin modified by a butene-1-containing modified ethylene copolymer.

[0051] It is particularly preferable that the matrix resin comprises (A) an impact-resistant polyamide resin comprising a blend of a polyamide resin and a propylene-containing modified ethylene copolymer, and (B) an impact-resistant polyamide resin comprising a blend of a polyamide resin and a butene-1-containing modified ethylene copolymer. This matrix resin is capable of providing high electroconductivity relative to the percentage of the electroconductive material (especially carbon black). In this case, the content of the impact-resistant polyamide resin (A) in the matrix resin is preferably 70 to 90% by weight, and the content of the impact-resistant polyamide resin (B) is preferably 5 to 30% by weight, because this proportion provides a good balance of modulus and impact strength of the composition.

[0052] The impact-resistant electroconductive polyamide resin composition for fuel tank caps according to the present invention can be produced by a method in which a mixture of the components dry-blended by a Henschel mixer or other preferable means is continuously kneaded by a known single- or twin-screw kneader and pelletized. In the composition of the present invention, one or more of the ordinarily used additives, for example, ultraviolet absorber (such as benzophenone), antioxidant, heat stabilizer (such as hindered phenol) and crystallization promotor (such as polyethylene glycol) may be added as required within limits not prejudicial to the object of the present invention.

[0053] As described above, the polyamide resin composition of the present invention shows excellent mechanical properties such as tensile modulus, bending modulus and Izod impact strength as well as a good molding workability. The fuel tank caps molded from the polyamide composition of the present invention are capable of discharging static electricity charged on the human body or clothes, with certainty within a given period of time.

EXAMPLES

[0054] The present invention is further illustrated by the following examples, which examples however are merely intended to be illustrative and not to be construed as limiting the scope of the invention. In the following Examples, all "parts" and "percents (%)" are by weight unless otherwise noted. The property evaluations in the Examples were made by the following methods.

(1) Bending modulus (bending strength): ASTM D790

(2) Izod impact strength: ASTM D256

(3) Volume resistivity (surface resistivity)

[0055] An injection molded 10 cm x 10 cm x 2 mm thick plate was set in a resistivity measuring cell mfd. by Yokokawa Hewlett Packard, Ltd., and its resistivity was measured. Resistivity above $10^5 \Omega$ was measured using High Resistance Meter mfd. by Yokokawa Hewlett Packard, Ltd., at an applying voltage of 500 V, and resistivity not more than $10^6 \Omega$ was measured using Digital Multimeter mfd. by Advantest Co., Ltd.

(Production of resin composition)

Example 1

(Production of modified polyethylene polymers)

[0056] 0.02 part of α, α -bis-1-butylperoxy-p-diisopropylbenzene and 0.4 part of maleic anhydride were added to 100 parts of an ethylene-propylene copolymer having a degree of crystallinity of 5% and a melt index (ML) of 0.35, and mixed by a Henschel mixer, and the mixture was kneaded by a 35 mm \varnothing single-screw kneader at 230°C and pelletized to obtain a modified polyolefin copolymer (hereinafter called modified polyethylene A).

[0057] Meanwhile, 0.025 part of α, α -bis-1-butylperoxy-p-diisopropylbenzene and 0.8 part of maleic anhydride were added to 100 parts of an ethylene-butene-1 copolymer having a degree of crystallinity of 20%, MI of 3.6 and a butene-1 content of 14 mol%, and mixed by a Henschel mixer, and the mixture was treated as described above to obtain a modified polyolefin copolymer (hereinafter called modified polyethylene B).

(Production of impact-resistant polyamide resins)

[0058] 20% of the said modified polyethylene A and small quantities (less than 1%) of the additives such as antioxidant and dispersant were blended with 80% of a nylon 6 resin (tradename: Novamide 1020) produced by Mitsubishi Engineering-Plastics Corporation and the blend was kneaded by the said kneader to obtain an impact-resistant polyamide resin A (hereinafter called impact-resistant resin A).

[0059] Meanwhile, 45% of the said modified polyethylene B and small quantities of additives such as antioxidant and dispersant were blended with 55% of a nylon 6 resin (trade name: Novamide 1010J) produced by Mitsubishi Engineering-Plastics Corporation and the blend was kneaded by the said kneader to obtain an impact-resistant polyamide resin B (hereinafter called impact-resistant resin B).

(Production of carbon black)

[0060] 500 g of furnace carbon black having a specific surface area of 40 m²/g, DBP absorption of 175 ml/100 g, a pH of 6.3, a volatile component of 1.80%, a total oxygen content of 30.6 mg/g and UV absorbance of 0.18, was put into a 30 cm \varnothing , 50 cm long cylindrical SUS kiln and the latter was rotated at a speed of 10 rpm. Nitrogen gas was introduced into the kiln from its central part at a rate of 10 l/min, and after the whole inside of the kiln has been perfectly substituted with CO₂, heating was started. Heating was conducted using an electric furnace covering the entire kiln for a period of 6 minutes while controlling it so that the carbon black temperature would reach 350 \pm 5°C. The properties of the obtained carbon black are shown in Table 1.

Table 1

Properties of carbon black	
DBP	175 ml/100 g

Table 1 (continued)

Properties of carbon black	
Specific surface area (measured by BET method)	43 m ² /g
PH	6.9
Volatiles	0.57%
Total oxygen	10.4 mg/g
UV absorbance	0.09

(Production of electroconductive composition)

[0061] 22% of the carbon black having the properties shown in Table 1 and 5% of N-n-butylbenzenesulfonamide (trade name: BBBSA, produced by Toray Corp.) were blended with 58.4% of the impact-resistant resin A and 14.6% of the impact-resistant resin B, and mixed for 10 minutes by a Henschel mixer (1,000 rpm).

[0062] Each mixture was kneaded by Toshiba Machinery kneader TEM-35 having a screw diameter of 35 mm under the conditions of kneading section temperature = 275°C, resin temperature = 270°C and feed rate = 4 kg/h, and the obtained strand was cooled with water and pelletized. The pellets were dried by a vacuum dryer at 70°C for 12 hours and subjected to the following injection molding.

[0063] The said pellets were injection molded by Japan Steel Works injection molder J-75ED under the conditions of cylinder temperature = 280°C, mold temperature = 80°C, screw speed = 120 rpm and injection pressure = 1,039 kg/m² to obtain the test pieces for evaluation. The results of the various property evaluations are shown in Table 3.

Example 2

[0064] The same procedure as defined in Example 1 was conducted except that the amount of the resin blended was changed to 65%, the amount of carbon black was changed to 30% and the amount of BBBSA was changed to 5% to obtain the test pieces for evaluation. The results of the evaluation tests are shown in Table 3.

Example 3

[0065] The same procedure as defined in Example 1 was conducted except that the amount of the impact-resistant resin A blended was changed to 65.7% and the amount of the impact-resistant resin B was changed to 7.3% to obtain the test pieces for evaluation. The results of the evaluation tests are shown in Table 3.

Example 4

[0066] The same procedure as defined in Example 1 was conducted except that Koechen Black International carbon black Koechen Black EC having the properties shown in Table 2 were used in an amount of 9.5% to obtain the test pieces for evaluation. In this example, the amount of the resin blended was 85.5% and the amount of BBBSA 5%. The results of the evaluation tests are shown in Table 3.

Table 2

Properties of carbon black	
DBP	360 ml/100 g
Specific surface area	800 m ² /g
PH	9.0
Volatiles	0.5%
Total oxygen	22.3 mg/g
UV absorbance	0.11

Example 5

[0067] The same procedure as defined in Example 1 was conducted except that two types of carbon black, namely 17.6% of carbon black used in Example 1 and 4.4% of carbon black used in Example 4 (totaling 22%) were used to obtain the test pieces for evaluation. The results of the evaluation tests are shown in Table 3.

Example 6

[0068] The same procedure as defined in Example 1 was conducted except that the amount of the impact-resistant resin A was changed to 43.8% and the amount of the impact-resistant resin B was changed to 29.2% to obtain the test pieces for evaluation. The results of the evaluation tests are shown in Table 3.

Example 7

[0069] The same procedure as defined in Example 1 was conducted except that the impact-resistant resin A alone was blended in an amount of 73% to obtain the test pieces for evaluation. The results of the evaluation tests are shown in Table 3.

Comparative Example 1

[0070] The same procedure as defined in Example 1 was conducted except that the impact-resistant resin A alone was used in an amount of 73% to obtain the test pieces for evaluation. The results of the evaluation tests are shown in Table 3.

Comparative Example 2

[0071] The same procedure as defined in Example 1 was conducted except that an impact-resistant polyamide resin C obtained by mixing 20% of the said modified polyethylene B and small quantities of the additives such as antioxidant and dispersant with 7.3% of the impact-resistant resin A and 80% of Du Pont nylon 66 "FE-3218" and kneading the mixture by the said kneader was blended in an amount of 65.7%. The results of the evaluation tests are shown in Table 3.

Table 3

	Bending modulus	Izod impact strength	Surface resistivity
Example 1	14500	46	1.1×10^9
Example 2	14000	41	6.3×10^2
Example 3	17100	46	2.8×10^9
Example 4	14400	42	7.3×10^6
Example 5	14100	43	8.2×10^3
Example 6	11500	48	8.9×10^9
Example 7	18600	38	5.6×10^{10}
Comparative Example 1	7570	29	9.3×10^9
Comparative Example 2	18500	8	1.3×10^9

(Manufacture of fuel tank caps)

Examples 8-14

[0072] A resin-made closure and a resin-made shell of a fuel tank cap (see FIG. 1) principally comprising a resin-made closure fitting on a filler neck and a resin-made shell were injection molded under the conditions shown in Table 4 below using the pellets of each of the impact-resistant electroconductive polyamide resin compositions obtained in Examples 1-7.

Table 4

Resin temperature	275°C
Mold temperature	40°C
Injection pressure	50 kg/cm ²
Injection time	1 hour
Dwell pressure	60 kg/cm ²
Retention time	6 seconds

[0073] Volume resistivity of the resin-made shell (outer shell) was measured according to ASTM D257 in the following way: As shown in FIG. 4, each outer shell (a) was held between the opposing electrodes (b) having attached to their ends an electroconductive rubber sheet with resistance of not more than 100 Ω , then a high resistance meter (mfd. by Advantest Co., Ltd.) was connected to the electrodes and volume resistivity of the shell was measured by applying a voltage of 500 V. The results show that the outer shells molded from the pellets of the impact-resistant electroconductive polyamide resin compositions obtained in Examples 1 to 7 had sufficient volume resistivity for practical use as a member of the fuel tank caps.

Claims

1. A polyamide resin composition comprising a polyamide resin, a modified ethylene copolymer, an amide-based dispersant and an electroconductive material,

said composition having not more than 10^{11} $\Omega \cdot \text{cm}$ of an intrinsic volume resistivity and not less than 30 KJ/cm² of an Izod impact strength measured according to ASTM D256.

2. A polyamide resin composition according to Claim 1, wherein the polyamide resin is nylon 6.
3. A polyamide resin composition according to Claim 2, wherein the reduced viscosity represented by η_{rel} of nylon 6 is 2.2 to 3.5.
4. A polyamide resin composition according to Claim 1, wherein the modified ethylene copolymer is the one containing propylene as repeating units, the one containing butene-1 as repeating units or a mixture thereof.
5. A polyamide resin composition according to Claim 1, wherein the amide-based dispersant is N-alkylarylsulfoneamide.
6. A polyamide resin composition according to Claim 1, wherein the electroconductive material is carbon black.
7. A polyamide resin composition according to Claim 6, wherein the carbon black has a total amount of oxygen from the volatiles of not more than 25 mg/g and a UV absorbance of not more than 0.15.
8. A polyamide resin composition according to Claim 6, wherein the carbon black is two or more types of carbon black having a different specific surface area of not less than 500 m²/g from each other.
9. A polyamide resin composition according to Claim 1, wherein the content of the modified ethylene copolymer is 10 to 120 parts by weight based on 100 parts by weight of the polyamide resin, the amount of the amide-based dispersant composition is 1 to 15% by weight based on the total composition, and the amount of the electroconductive material is 8 to 35% by weight based on the total composition.
10. A polyamide resin composition according to Claim 1, wherein the modified ethylene copolymer is the one containing propylene as repeating units, and the content of the propylene-containing modified ethylene copolymer is 10 to 40 parts by weight based on 100 parts the polyamide resin, the amount of the amide-based dispersant composition is 1 to 15% by weight based on the total composition, and the amount of the electroconductive material is 8 to 35% by weight based on the total composition.

11. A polyamide resin composition according to Claim 1, wherein the modified ethylene copolymer is the one containing butene-1 as repeating units, and the content of the butene-1-containing modified ethylene copolymer is 10 to 40 parts by weight based on 100 parts the polyamide resin, the amount of the amide-based dispersant composition is 1 to 15% by weight based on the total composition, and the amount of the electroconductive material is 8 to 35% by weight based on the total composition.
12. A polyamide resin composition comprising:
- 70 to 95% by weights of an impact-resistant polyamide resin (A) comprising 100 parts by weight of polyamide resin and 10 to 40 parts by weight of propylene-containing modified ethylene copolymer,
5 to 30% by weights of an impact-resistant polyamide resin (B) comprising 100 parts by weight of polyamide resin and 50 to 120 parts by weight of propylene-containing modified ethylene copolymer,
1 to 15% by weights of an amide-based dispersant, and
8 to 35% by weights of an electroconductive material.
13. A fuel tank cap comprising an impact-resistant electroconductive polyamide resin composition comprising a polyamide resin, a modified ethylene copolymer, an amide-based dispersant and an electroconductive material, said composition having a volume resistivity of not more than $10^{11} \Omega \cdot \text{cm}$ and an Izod impact strength according to ASTM D256 of not less than 30 KJ/m^2 .
14. A fuel tank cap according to Claim 13, which further comprises a resin-made closure fitted on a fuel filler neck and a resin-made shell covering the upper part of said closure, and having a static electricity discharge route, wherein at least said shell comprises the polyamide resin compositions as defined in Claim 13.
15. A fuel tank cap according to Claim 14, wherein both of the resin-made closure and the resin-made shell comprises the polyamide resin compositions as defined in Claim 13.
16. A fuel tank cap according to Claim 13, wherein the polyamide resin is nylon 6.
17. A fuel tank cap according to Claim 16, wherein the reduced viscosity of the nylon 6 as defined by η_{rel} is 2.2 to 3.5.
18. A fuel tank cap according to Claim 13, wherein the modified ethylene copolymer is the one containing propylene as repeating units, the one containing butene-1 as repeating units or mixture thereof.
19. A fuel tank cap according to Claim 13, wherein the amide-based dispersant is N-alkylarylsulfoneamide.
20. A fuel tank cap according to Claim 13, wherein the electroconductive material is carbon black.
21. A fuel tank cap according to Claim 20, wherein the carbon black has a total amount of oxygen from the volatiles of not more than 25 mg/g and a UV absorbance of not more than 0.15.
22. A fuel tank cap according to Claim 21, wherein the carbon black is two or more types of carbon black having a different specific surface area of not less than $500 \text{ m}^2/\text{g}$ from each other.
23. A fuel tank cap according to Claim 13, wherein the content of the modified ethylene copolymer is 10 to 120 parts by weight based on 100 parts by weight of the polyamide resin, the amount of the amide-based dispersant composition is 1 to 15% by weight based on the total composition, and the amount of the electroconductive material is 8 to 35% by weight based on the total composition.
24. A fuel tank cap according to Claim 13, wherein the modified ethylene copolymer is the one containing propylene as repeating units, and the content of the propylene-containing modified ethylene copolymer is 10 to 40 parts by weight based on 100 parts the polyamide resin, the amount of the amide-based dispersant composition is 1 to 15% by weight based on the total composition, and the amount of the electroconductive material is 8 to 35% by weight based on the total composition.
25. A fuel tank cap according to Claim 13, wherein the modified ethylene copolymer is the one containing butene-1 as repeating units, and the content of the butene-1-containing modified ethylene copolymer is 10 to 40 parts by weight based on 100 parts the polyamide resin, the amount of the amide-based dispersant composition is 1 to 15% by

weight based on the total composition, and the amount of the electroconductive material is 8 to 35% by weight based on the total composition.

- 5 26. A fuel tank cap comprising polyamide resin composition as defined in Claim 12.
27. Use of an impact-resistant electroconductive polyamide resin composition comprising a polyamide resin, a modified ethylene copolymer, an amide-based dispersant and an electroconductive material,
- 10 said composition having not more than $10^{11} \Omega \cdot \text{cm}$ of an intrinsic volume resistivity and not less than 30 KJ/cm² of an Izod impact strength measured according to ASTM D256, for producing fuel tank caps.

15

20

25

30

35


40

45

50

55

FIG.1



1 p 15

FIG.2




FIG.3





FIG.4





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 12 4445

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
Y	DATABASE WPI Section Ch, Week 8749 Derwent Publications Ltd., London, GB; Class A17, AN 87-345608 XP002098749 & JP 62 250053 A (MITSUBISHI PETROCHEMICAL CO LTD), 30 October 1987 * abstract *	1-12	C08L77/00 C08K3/04 B60K15/04
Y	DATABASE WPI Section Ch, Week 8328 Derwent Publications Ltd., London, GB; Class A23, AN 83-708293 XP002098750 & JP 58 093756 A (MITSUBISHI CHEM IND LTD) , 3 June 1983 * abstract *	1-12	
Y	DATABASE WPI Section Ch, Week 7723 Derwent Publications Ltd., London, GB; Class A17, AN 77-40758Y XP002098751 & JP 52 052957 A (ASAHI CHEM IND CO LTD) , 28 April 1977 * abstract *	1-12	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C08L C08K B60K
Y	PATENT ABSTRACTS OF JAPAN vol. 014, no. 350 (C-0744), 27 July 1990 & JP 02 127467 A (ASAHI CHEM IND CO LTD), 16 May 1990 * abstract *	1-12	
A	WO 95 22579 A (DU PONT) 24 August 1995 * page 3, line 36 - page 4, line 34 * * page 5, line 30 - page 5, line 36 * * claim 1 *	1-27	
-/--			
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 1 April 1999	Examiner Heidenhain, R
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03.92 (P4/C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 12 4445

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	EP 0 218 063 A (BASF AG) 15 April 1987 * claims 1,2 *	1-27	
A	EP 0 754 731 A (MITSUI PETROCHEMICAL IND) 22 January 1997 * claims 1,2 *	1-27	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 1 April 1999	Examiner Heidenhain, R
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/92 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 12 4445

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

01-04-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9522579 A	24-08-1995	US 5670575 A	23-09-1997
EP 0218063 A	15-04-1987	DE 3531269 A	12-03-1987
		JP 62053372 A	09-03-1987
EP 0754731 A	22-01-1997	CA 2181124 A	14-01-1997
		CN 1141320 A	29-01-1997
		JP 9087475 A	31-03-1997

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.